

SCB CH 35

Carbon Ceramic Charcoal (Color Stable)

Automotive Window Films

Carbon Charcoal 35%	
Visual Light Transmission	35%
Solar Transmission	49.1%
Solar Absorption	45.3%
Solar Reflectance	5.6%
Visual Light Reflectance / Interior	5.4%
Visual Light Reflectance / Exterior	5.2%
IR Transmission(900~1000nm)	59%
IR Transmission(780~2500nm)	64%
UV Rejection	99% up
Shading Coefficient	0.76
Solar Heat Gain Coefficient (SHGC)	0.69
Total Solar Energy Rejected (TSER)	31%