

SCB CH 50

Carbon Ceramic Charcoal (Color Stable)

Automotive Window Films

Carbon Charcoal 50%	
Visual Light Transmission	50%
Solar Transmission	60.9%
Solar Absorption	33.0%
Solar Reflectance	6.1%
Visual Light Reflectance / Interior	6.1%
Visual Light Reflectance / Exterior	5.9%
IR Transmission(900~1000nm)	69%
IR Transmission(780~2500nm)	73%
UV Rejection	99% up
Shading Coefficient	0.82
Solar Heat Gain Coefficient (SHGC)	0.73
Total Solar Energy Rejected (TSER)	27%