# SWI NC 15

## IR Nano-Ceramic (Color Stable)

# Automotive Window Films

| IR Nano-Ceramic 15% | |
|---|---|
| Visual Light Transmission | 15% |
| Solar Transmission | 24.0% |
| Solar Absorption | 71.2% |
| Solar Reflectance | 4.8% |
| Visual Light Reflectance / Interior | 4.8% |
| Visual Light Reflectance / Exterior | 4.6% |
| IR Transmission(900~1000nm) | 34% |
| IR Transmission(780~2500nm) | 26% |
| UV Rejection | 99% up |
| Shading Coefficient | 0.54 |
| Solar Heat Gain Coefficient (SHGC) | 0.46 |
| Total Solar Energy Rejected (TSER) | 54% |

This information is the best currently available on the subject. The result should, however, only be regarded as a general guide to material properties and not as a guarantee. Some of the properties can be changed as a result of supplier's effort to improve the quality or production efficiency of the subject.