

SWI NC 20

IR Nano-Ceramic (Color Stable)

Automotive Window Films

IR Nano-Ceramic 20%	
Visual Light Transmission	26%
Solar Transmission	28.0%
Solar Absorption	67.1%
Solar Reflectance	4.9%
Visual Light Reflectance / Interior	5.1%
Visual Light Reflectance / Exterior	4.9%
IR Transmission(900~1000nm)	38%
IR Transmission(780~2500nm)	29%
UV Rejection	99% up
Shading Coefficient	0.57
Solar Heat Gain Coefficient (SHGC)	0.49
Total Solar Energy Rejected (TSER)	51%