

SWI NC 35

IR Nano-Ceramic (Color Stable)

Automotive Window Films

IR Nano-Ceramic 35%	
Visual Light Transmission	37%
Solar Transmission	38.1%
Solar Absorption	56.7%
Solar Reflectance	5.2%
Visual Light Reflectance / Interior	5.4%
Visual Light Reflectance / Exterior	5.4%
IR Transmission(900~1000nm)	48%
IR Transmission(780~2500nm)	37%
UV Rejection	99% up
Shading Coefficient	0.63
Solar Heat Gain Coefficient (SHGC)	0.54
Total Solar Energy Rejected (TSER)	46%