

SWI NC 40

IR Nano-Ceramic (Color Stable)

Automotive Window Films

IR Nano-Ceramic 40%	
Visual Light Transmission	42%
Solar Transmission	40.4%
Solar Absorption	54.0%
Solar Reflectance	5.6%
Visual Light Reflectance / Interior	5.9%
Visual Light Reflectance / Exterior	5.9%
IR Transmission(900~1000nm)	50%
IR Transmission(780~2500nm)	37%
UV Rejection	99% up
Shading Coefficient	0.66
Solar Heat Gain Coefficient (SHGC)	0.56
Total Solar Energy Rejected (TSER)	44%